

INDICATIVE CHEMICAL RESISTANCE CHART

X = GLASS FIBRE REINFORCED NYLON 6 (15% and 30%)

CHEMICAL TYPE	RESISTANCE LEVEL		
	GOOD	OK - BUT CHECK FURTHER	BAD - TRY TO AVOID
Acids Weak			X
Acids Strong			X
OrganicAcids Weak		X	
OrganicAcidsStrong			X
Bases Weak	X		
Bases Strong		X	
Bleach			X
CHEMICAL TYPE	RESISTANCE LEVEL		
Automotive Fuel	X		
Automotive Lubricants	X		
Hydraulic Fluids	X		
CHEMICAL TYPE	RESISTANCE LEVEL		
Solvents		X	
Hydrocarbons	X		
Halogens			X
Alcohols	X		
Aldehydes	X		
Amines	X		
Esters	X		
Ethers	X		
Ketones	X		
CHEMICAL TYPE	RESISTANCE LEVEL		
Detergents	X		
Oxidizing Agents			X
Weak Hydrogen Peroxide		X	
Phenols			X

PLEASE NOTE: This chart is intended as a basic guide only. The resistance to a given chemical will vary with temperature & concentrations. Some chemicals within the group mentioned may result in different rating. For further information, please contact us with your specific question.